

Guilford of Maine Crosstown Acoustic Fabric



Description

The Guilford of Maine Crosstown Acoustic Fabric weaves strands of color into a geometric crisscross pattern to develop unique colors that are both elegant and well balanced. Choose from colors like cement, mystic, chamois, fieldstone and stucco to generate remarkable designs. The fabric is used to wrap an acoustical substrate or other absorptive material to produce a clean and beautiful finish for any project.

Features

- Acoustical panel fabric
- Cleanable with water based cleaning agents

Technical Characteristics

Size:	66" wide x 36" yard
Materials:	77% Pre-consumer recycled polyester 23% Post-consumer recycled polyester
Weight:	13.6 +/- 1.0 oz./ linear yard
Pattern:	Large Scale
Repeat Vertical:	12.5"
Repeat Horizontal:	16.2"
Backing:	None
Treatment:	None
Fire Rating:	Class 1 or A per ASTM E84
Breaking Strength:	250 lbf min. warp 150 lbf min. fill (ASTM D5034)
Colorfastness to Light:	Grade 4 min. at 40 hours (AATCC 16 Option 3)
Colorfastness to Crocking:	Grade 4 min. dry Grade 3 min. wet (AATCC 8)
Acoustic Transparency:	95%
Bleach Cleanable:	No

Colors may vary between dye lots.

Revised: 2025-04-30

Acoustic Performance for Panel Applications (ISO 10534-2)

Frequency (Hz)	NRC
250	0.03
500	0.03
1000	0.06
2000	0.12
NRC of fabric in front of anechoic termination	0.05
NRC of anechoic termination	1.00

This test measures the NRC of fabric in front of anechoic termination (NRC of anechoic termination = 1.00). The test is done using an impedance tube with a sound source connected to one end and the test sample mounted in the tube at the other end.

For more information, please consult:
<https://www.iso.org/standard/22851.html>